



TECHNICAL INSTRUCTION FOR CEMENT CEM III/B 32,5N SR LH

Product: Sulfate resistant cement of low heat of hydration CEM III/B 32,5N SR LH

Strength rank: 32,5N according to norm EN 197-1:2011.

Product description and application:

CEM III/B 32,5 N SR LH is sulfate resistant cement of low heat of hydration with 66-80 % slag and 20-34% clinker (including binding regulator (natural gypsum). It is used for application in demanding construction projects where high sulfate resistance is required: concrete works in warm climate, structures in humid and aggressive environment rich in sulfates, bridge base, maritime and littoral objects, road works, irrigation systems, sewage and drainage systems.

Instructions for use:

When dosing it is necessary to hold on to concrete structure project. When preparing concrete mixture one must use results of first concrete testing, concrete project and carry out prescribed concrete quality control.

Characteristics

Characteristic values of mechanical, physical and chemical properties for cement CEM III/B 32,5N SR LH and requirements according to norm EN 197-1:2011.

Mechanical and physical properties:	CEM III/B 32,5N SR LH	Norm requirement:
Start of binding (min)	230	≥ 75
Volume stability acc. to Le Chatelier (mm)	0,3	≤ 10
Pressure strength after 7 days (MPa)	20	≥ 16
Pressure strength after 28 days (MPa)	41	≥ 32,5 ≤52,5
Heat of hydration (J/g)	210	≤ 270
Chemical properties:		
SO3 (%)	2,2	≤ 4,0
CI (%)	0,05	≤ 0,1
Loss on calcination (%)	0,5	≤ 5,0
Content of insoluble residue (%)	0,7	≤ 5,0

Quality control:

Production process is part of integrated management system certified according to international norms ISO 9001:2015 and ISO 14001:2015, ISO 45001:2018. and ISO 50001:2018. In addition to regular internal quality control in all phases of production process Institute for Civil Engineering in Zagreb Croatia carries out independent control. Product is subject to compliance proof according to EN 197-1:2011.

Certificate of constancy of performance: Issued by Institut IGH d.d. Zagreb

Declaration of performance: 2477-CPR-2766-NC06-001 from 09/01/2020. Declaration of performance available at: www.nexe.hr/en / PRODUCTS&SERVICES/ Cement/ Declaration of performance CEM III/B 32,5N SR LH (number: 2477-CPR-2766-NC06-001).

Delivery, transport and storage:

Cement is delivered in bulk in cisterns.

Bulk cement is delivered in dry and clean cisterns without organic and anorganic impurities. Bulk cement should be storaged in concrete or metal silos isolated from atmospheric agents. It is recommended to fill the same silo with one type of cement, i.e. not mix different types of cement.

Best before: 3 months from date of despatch on Despatch note, if conditions of transport and storage are met.

COUNTRY OF ORIGIN: REPUBLIC OF CROATIA

Technical information from this instruction is given according to latest information we dispose of, as general instructions only and are subject to change without previous notice. Information regarding cement content and property values are characteristic and approximate.





DANGER

H318	Causes	serious	eve	damage

H315 Causes skin irritation

H317 May cause an allergic skin reaction

H335 May cause respiratory irritation

P102 Keep out of reach of children

P280 Wear protective gloves/protective clothing/eye protection/face protection

P305+P351+P338+P310:

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a POISON CENTER or doctor/physician

P302+P352+P333+P313:

IF ON SKIN: Wash with plenty of soap and water. If skin irritation or rash occurs: Get medical advice/attention

P261+P304+P340+P312:

Avoid breathing dust/fume/gas/mist/vapours/spray. IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. Call a POISON CENTER or doctor/physician if you feel unwell.

P501 Dispose of contents/container according to national regulations.